



CITGO PREMIUM COUPLING GREASE

Date 08/17

DESCRIPTION: CITGO Premium Coupling Grease is specially formulated with a lithium/polymer thickener in premium high viscosity base oils to provide excellent resistance to oil separation when used in high-speed grease lubricated couplings.

- BENEFITS:**
- **Minimal Oil Separation:** CITGO Premium Coupling Grease exhibits very low oil separation in ASTM D4425 high-speed centrifuge test.
 - **Excellent adhesion:** This product is fortified with heavy base oils and a polymer additive to provide outstanding adhesion.
 - **Load Carrying:** High viscosity base oils are utilized to provide outstanding load carrying ability.
 - **Versatility:** This product is recommended for all types of grease lubricated couplings used in industrial equipment. It meets or exceeds the requirements of AGMA CG-1, CG-2 & CG-3 type coupling greases.
 - **Oxidation Resistance:** Premium Coupling Grease provides outstanding resistance to oxidation.
 - **Water Resistance:** This product is highly resistant to both water washout and water spray-off.
 - **Grease Compatibility:** Premium Coupling Grease is formulated with a lithium/polymer thickener system that is compatible with many other coupling greases that are currently on the market.

APPLICATIONS: Premium Coupling Grease is recommended for grease lubricated couplings including geared couplings, grid couplings and flexible chain couplings. Because of its water resistance and high viscosity base oils it may be suitable for use in applications subjected to high water wash, heavy loads and low speeds. Consult owners manual for proper lubricant recommendation.

TYPICAL PROPERTIES:**CITGO PREMIUM COUPLING GREASE**

SAP Code	655231001
NLGI Grade	0-1
Worked-60 Penetration	325-355
Grease Type	Lithium/Polymer
Color	Amber
Texture	Smooth, Adhesive
Dropping Point, °F(°C), ASTM D2265	336 (169)
Rust Protection, ASTM D1743	Pass
Copper Corrosion, ASTM D4048	1B
Centrifugal Oil Separation, ASTM D4425	<8%
Oxidation, ASTM D942, psi loss @ 100 hrs	3
Water Spray Off, ASTM D4049, % Loss	<2%
Four-Ball Wear, ASTM D2266, mm	0.4
Four-Ball Weld, ASTM D2596, kgf	400
Four-Ball Load Wear Index, ASTM D2596, kg	63.4
Oil Viscosity @ 100°C, cSt., with Oil Sol. Additives	191
Oil Viscosity @ 40°C, cSt., with Oil Sol. Additives	4240
Viscosity Index with Oil Sol. Additives	148

CITGO, and CompressorGard are registered trademarks of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners.

Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.